



Powder Free Extra Length Ambidextrous Non-Sterile 30 cm Nitrile Gloves with Textured Fingertips

PPE Category III (Complex Design) according to Council Directive 89/686/EEC

Fully compliant to the latest PPE norms - EN374: 2003 "Protective gloves against chemicals and micro-organisms"

PRODUCT INFORMATION

Size	Catalogue Numbers	Applicable Norms with Pictograms				
Extra Small (XS/6)	67 6251	EN374: 2003	EN374: 2003			
Small (S/7)	67 6252		1	€ 0120*		
Medium (M/8)	67 6253		Level 3			
Large (L/9)	67 6254	EN420: 2003 + A1:2009				
Extra Large (XL/10)	67 6255	Also meets or exceeds EN455-1: 2000, EN455-2: 2009+A1:2011,				
		 EN455-3:2006 & EN455-4:2009 relating to Council Directive 93/42/EEC for Medical Devices 				

^{*} SGS UK Ltd (Notified Body No: 0120), Unit 202B Worle Parkway, Weston-super-Mare, BS22 6WA, United Kingdom

Material: Proprietary multi-polymer formulation (Acrylonitrile Butadiene with blend of polychloroprene), based on

Twinshield[™] technology. Contains no natural rubber latex.

Design: Double barrier protection afforded by orange outer layer combined with white inner-lining.

Ambidextrous, beaded cuff and with textured fingertips.

290mm, min.

Packaging: Fifty (50) gloves per dispenser. Dispenser is varnished for enhanced compatibility with laboratory

environments. Gloves are flat-packed. Ten (10) dispensers per case. Packed in a reinforced single-

walled shipping case.

- Length

PHYSICAL PROPERTIES								
Characteristics		Value	Test Method					
	<u> </u>			1				
Freedom from holes		<0.65 AQL ¹			EN374: 2003			
¹ AQL as defined per ISO 2859 for sam Tensile Properties	Tensile Strength (min) Typical	Ultimate					
rensite Properties	rensite strength (illili) Typicat	Elongation					
- Before Aging	6.0N, min.	7.0N	500%, min.	EN455-2: 2009 + A1:2011, ASTM D 04 and ASTM D412-06ae2				
- After Accelerated Aging	6.0N, min.	8.0N	400%, min.	04	and ASTM D412-00de2			
Dimensional	Measured Point	Mm	mil		,			
- Nominal Thickness	Middle Finger	0.17	6.6		ASTM D3767-03			
	Palm	0.14	5.5					
	Cuff	0.10	4.0					

300mm, typical

EN420: 2003 + A1: 2009

Palm Widths

- Nominal Width (mm)	XS/6	S/7	M/8	L/9	XL/10	EN455-2: 2009 + A1: 2011
	≤80	85	95	105	≥110	

Hand Circumference

- Nominal circumference (mm)	XS/6	S/7	M/8	L/9	XL/10	EN420: 2003 +A1:2009
	152	178	203	229	254	

ADDITIONAL DATA

- Biocompatibility demonstrated by Buehler and Primary Skin Irritation Tests.
- Non-detectable levels of chemical allergens using aqueous solution extraction (Phosphate buffered solution) and High Performance Liquid Chromatography (HPLC) assay method for quantitative analysis.
- Accelerator-free to minimize the risk of Allergic Contact Dermatitis (also known as Type IV, Delayed Hypersensitivity or Chemical Allergy).
- **Powder free** to minimize the potential consequences of powder-borne dermatitis. Residual powder content is 1.0 mg/glove (typical) with a limit of 2.0 mg/glove (ISO 21171: 2006 "Medical gloves Determination of removable surface powder").
- Micro organism and virus resistant passes highest level of micro organism resistance per EN374-2: 2003 (Performance level 3, AQL <0.65 and inspection level G1 according to 1000ml water test) and passes viral penetration test using Phi-X174 bacteriophage (ISO 16604: 2004 Procedure B & ASTM F1671-97b).
- Tested for electrostatic properties according to EN1149-1/2/3 & 5
- Extensively tested for chemical permeation according to EN374-3: 2003 (please refer to chemical resistance guide on website www.shieldscientific.com/public/chemical-resistance-guide)

QUALITY SYSTEMS

Manufactured in accordance with ISO 9001:2008 and ISO 13485:2003.

"SHIELDskin™, A revolution in Glove Technology"



R & L Slaughter Ltd.
Units 11 & 12, Upminster Trading Park,
Warley St. Upminster. RM14 3PJ
Tel: 01708 227140 Fax: 01708 228728
email: sales@slaughter.co.uk
website www.slaughter.co.uk